

8. (Amended) Multilayer manufactured articles according to claim 1, wherein on the top of layer A) a layer A1) is placed based on copolymers of ethylene with chlorotrifluoroethylene, and/or tetrafluoroethylene, not containing the acrylic monomer (a), and/or on the top of layer B), a layer B1) is placed based on polyamide having an amount of  $\text{-NH}_2$  end groups lower than  $40\mu\text{eq/g}$ .

9. (Amended) Multilayer manufactured articles according to claim 1, under the form of sheath-core fibers.


10. (Amended) Fuel lines formed by multilayers according to claim 1, wherein at least the internal layer in contact with the liquid fuel is made conductive by incorporation of graphite and/or carbon black.

#### REMARKS

Claims 1-10 are pending in this application. By this Amendment, claims 3-10 are amended to correct the multiple dependencies thereof and to place this application into better condition for examination. No new matter has been added.

In the event that there are any fees due with respect to the filing of this paper,  
please charge Deposit Account No. 01-2300.

Respectfully submitted,

  
Douglas H. Goldhush  
Registration No. 33,125

**Customer No. 004372**  
ARENT FOX KINTNER PLOTKIN & KAHN, PLLC  
1050 Connecticut Avenue, N.W.,  
Suite 400  
Washington, D.C. 20036-5339  
Tel: (202) 857-6000  
Fax: (202) 638-4810

DHG:scc

Enclosures: Marked-up Copy of Amended Claims

204060 548800 10086845 030402

**MARKED-UP COPY OF AMENDED CLAIMS**  
**ATTY. DOCKET NO. 108910-00057**

3. (Amended) Multilayer manufactured articles according to claim 1 [and 2], wherein the thermoprocessable copolymers of layer A) are formed by:

- from 10 to 70% by moles, preferably from 35 to 55% of ethylene;
- from 30 to 90% by moles, preferably from 45 to 65%, of a fluorinated monomer selected from tetrafluoroethylene, chlorotrifluoroethylene, or mixtures thereof, preferably chlorotrifluoroethylene (CTFE);
- from 0.05% to 15% by moles of the acrylic comonomer (a) referred to the sum of the previous monomers, preferably n-butylacrylate.

4. (Amended) Multilayer manufactured articles according to [claims 1-3] claim 1, wherein layer A) is formed by a blend of the copolymers of layer A) and the same copolymers without the acrylic monomer, provided that the blend contains an amount of acrylic monomer (a) in the range 0.01% - 15% by moles with respect to the total sum of the monomers of ethylene and of CTFE and/or TFE of the blend.

5. (Amended) Multilayer manufactured articles according to [claims 1-4] claim 1, wherein the polyamides of layer B) are formed by a blend of polyamides having different contents of -NH<sub>2</sub> end groups provided that the blend contains an amount of -NH<sub>2</sub> end groups higher than 40 µeq/g.

10086845-030402  
204020-54898007

6. (Amended) Multilayer manufactured articles according to [claims 1-5] claim 1, wherein layer B) is a polyamide having an amount of  $\text{-NH}_2$  end groups lower than 40  $\mu\text{eq/g}$ , blended with 0.01-5% by weight, preferably 0.1-2% by weight, of one or more diamines.

7. (Amended) Multilayer manufactured articles according to [claims 1-6] claim 1, wherein the diamines are selected from the group formed by hexamethyldiaminecarbamate, N,N' -dicinnamylidene-1,6 hexandiamine, dodecylamine and decylamine, para-xylyldiamine.

8. (Amended) Multilayer manufactured articles according to [claims 1-7] claim 1, wherein on the top of layer A) a layer A1) is placed based on copolymers of ethylene with chlorotrifluoroethylene, and/or tetrafluoroethylene, not containing the acrylic monomer (a), and/or on the top of layer B), a layer B1) is placed based on polyamide having an amount of  $\text{-NH}_2$  end groups lower than 40  $\mu\text{eq/g}$ .

9. (Amended) Multilayer manufactured articles according to [claims 1-8] claim 1, under the form of sheath-core fibers.

10. (Amended) Fuel lines formed by multilayers according to [claims 1-8] claim 1, wherein at least the internal layer in contact with the liquid fuel is made conductive by incorporation of graphite and/or carbon black.